

Technical information **ROEDURTHERM AS-C**  
(antistatic base material)

Mechanical Properties	Norm	Unit	Values
Flexural strength	ISO 178	MPa	>380
Compression strength, RT	ISO 604	MPa	500

Electrical Properties	Norm	Unit	Values
Surface resistance	IEC 61340-5-1	Ohm	10E+5-10E+10
Spec. conductance	IEC93	kOhm/cm	0,5-50

Thermic Properties	Norm	Unit	Values
Thermal conductivity	DIN 52612	W/mK	0,3
Thermal decomposition temperature		°C	>370
Short-term temperature capacity		°C	300

Physical Properties	Norm	Unit	Values
Density	ISO 1183	g/cm <sup>3</sup>	1,9
Water absorption (24h 23°C)	ISO 62	Mg/%	10/0,03
Chemical resistance			Very good

Thickness	Tolerance to nominal thickness
3 – 14 mm	According to DIN 40606

**Anschrift**

RÖSNICK GmbH  
St.-Florian-Str. 6  
50181 Bedburg

**Kontaktdaten**

Fon +49 (0)2272 - 91 81 70  
Mail [info@roesnick.com](mailto:info@roesnick.com)  
Web [www.roesnick.com](http://www.roesnick.com)

**Bankverbindungen**

VR Bank eG, Bergisch Gladbach  
IBAN: DE57 3706 2600 3646 5360 13  
BIC: GENODE33PAF

Commerzbank AG, Köln  
IBAN: DE44 3708 0040 0429 1645 00  
BIC: DRESDEFF370