

As of 04.2023

Technical data sheet – Non-stick coating K10101

(Suitable for ROEDURTHERM E-300 AS-HT, AS-C and AS-I)

Description:

K10101 is a tribologically effective coating based on PTFE. The part is thermally or chemically degreased

prior to coating. In order to increase the coating bond to subsurface, sandblasting is recommended.

After coating the surface of the part is slightly roughened, feels like wax, and has a greyish color. K10101

is characterized by a good wear resistance and was developed especially for high-temperature applications. The product can be applied to plastic and/or all metallic surfaces.

Physical properties:

Color:	Grey
Layer thickness:	20-30µm
Recommended operating temperature:	Long-term -40 to 260°C
Food authorization:	No, manufactured acc. to EG 2023/2006
Electrostatic discharge capacity:	< 10 ⁸ Ohm
Anti-sticking properties:	Low
Chemical resistance:	Resistant against water, several mineral oils
Abrasion resistance:	Conditionally resistant
Pencil hardness acc. to DIN EN 13523-4:	HB
Water contact angle:	85
Dynamic sliding friction coefficient:	0,14
Adhesion acc. to DIN EN ISO 2409:	GT0
Mandril bending test DIN EN ISO 1519:	2,5

Typical areas of application:

Soldering frames, soldering masks, coating frames

Address

RÖSNICK GmbH
St.-Florian-Str. 6
50181 Bedburg

Contact Details

Phone +49 (0) 2272 91 81 70
Mail info@roesnick.com
Web www.roesnick.com

Bank Details

VR Bank eG Bergisch Gladbach
IBAN DE57 3706 2600 3646 13
BIC GENODE33PAF

Commerzbank AG Cologne
IBAN DE44 3708 0040 0429 1645 00
BIC DRESDEFF370

As of 04.2023

Application oriented pilot tests are strictly necessary!

All technical data are based on supplier's data and own examinations and experiences. They are not binding and do not oblige us to any guarantee. They are exclusively intended as information for technicians and application engineers at own risk.

Address

RÖSNICK GmbH
St.-Florian-Str. 6
50181 Bedburg

Contact Details

Phone +49 (0) 2272 91 81 70
Mail info@roesnick.com
Web www.roesnick.com

Bank Details

VR Bank eG Bergisch Gladbach
IBAN DE57 3706 2600 3646 13
BIC GENODED1PAF

Commerzbank AG Cologne
IBAN DE44 3708 0040 0429 1645 00
BIC DRESDEFF370