

As of 04.2023

Technical information ROEDURTHERM AS-C (antistatic base material)

Mechanical Properties	Norm	Unit	Values
Flexural strength	ISO 178	MPa	>380
Compression strength, RT	ISO 604	MPa	500

Electrical Properties	Norm	Unit	Values
Surface resistance	IEC 61340-5-1	Ohm	10E+5-10E+10
Spec. conductance	IEC93	kOhm/cm	0,5-50

Thermic Properties	Norm	Unit	Values
Thermal conductivity	DIN 52612	W/mK	0,3
Thermal decomposition temperature		°C	>370
Short-term temperature capacity		°C	300

Physical Properties	Norm	Unit	Values
Density	ISO 1183	g/cm ³	1,9
Water absorption (24h 23°C)	ISO 62	Mg/%	10/0,03
Chemical resistance			Very good

Thickness	Tolerance to nominal thickness
3 – 14 mm	According to DIN 40606

Address

RÖSNICK GmbH
St.-Florian-Str. 6
50181 Bedburg

Contact Details

Phone +49 (0) 2272 91 81 70
Mail info@roesnick.com
Web www.roesnick.com

Bank Details

VR Bank eG Bergisch Gladbach
IBAN DE57 3706 2600 3646 13
BIC GENODED1PAF

Commerzbank AG Cologne
IBAN DE44 3708 0040 0429 1645 00
BIC DRESDEFF370